



SOLVAY
asking more from chemistry®

Ryton® PPS Processing Comparison

Ryton® PPS R, BR, XE and XK grades

Material Information	R-7-120NA/ BR111	R-4-200NA/ R-4-220NA	R-4-230NA	XE3035/ XE4050/ XE5030	XK2340
Temperature					
Barrel temperature					
Rear	293–304 °C (560–580 °F)	293–304 °C (560–580 °F)	293–304 °C (560–580 °F)	293–304 °C (560–580 °F)	265–282 °C (510–540 °F)
Middle	304–316 °C (580–600 °F)	299–310 °C (570–590 °F)	299–310 °C (570–590 °F)	299–310 °C (570–590 °F)	271–288 °C (520–550 °F)
Front	316–327 °C (600–620 °F)	316–327 °C (600–620 °F)	304–316 °C (580–600 °F)	316–327 °C (600–620 °F)	277–293 °C (530–560 °F)
Nozzle	293–327 °C (580–620 °F)	293–321 °C (580–610 °F)	304–316 °C (580–600 °F)	293–321 °C (580–610 °F)	277–288 °C (530–550 °F)
Melt temperature (air purge)	329–335 °C (625–635 °F)	310–329 °C (610–625 °F)	316–321 °C (600–610 °F)	310–329 °C (610–625 °F)	288–296 °C (550–565 °F)
Thermolator set temp.					
Fixed	141–163 °C (285–325 °F)	141–163 °C (285–325 °F)	141–163 °C (285–325 °F)	141–163 °C (285–325 °F)	93–121 °C (150–300 °F)
Moving	141–163 °C (285–325 °F)	141–163 °C (285–325 °F)	141–163 °C (285–325 °F)	141–163 °C (285–325 °F)	93–121 °C (150–300 °F)
Mold steel temperature					
Fixed	135–149 °C (275–300 °F)	135–149 °C (275–300 °F)	135–149 °C (275–300 °F)	135–149 °C (275–300 °F)	60–135 °C (140–275 °F)
Moving	135–149 °C (275–300 °F)	135–149 °C (275–300 °F)	135–149 °C (275–300 °F)	135–149 °C (275–300 °F)	60–135 °C (140–275 °F)
Drying	135–163 °C (275–325 °F)	135–163 °C (275–325 °F)	135–163 °C (275–325 °F)	80–85 °C (175–185 °F)	80 °F (175 °C)
Pressure					
Peak pressure at cut-off	Part dependent	Part dependent	Part dependent	Part dependent	Part dependent
Boost pressure (1 st stage)	13.8+ bar (200+ psi) > peak pressure at cut-off	13.8+ bar (200+ psi) > peak pressure at cut-off	13.8+ bar (200+ psi) > peak pressure at cut-off	13.8+ bar (200+ psi) > peak pressure at cut-off	13.8+ bar (200+ psi) > peak pressure at cut-off
Pack pressure (2 nd stage)	60–75 % of peak at C.O. or 52 bar (750 psi) min.	60–75 % of peak at C.O. or 52 bar (750 psi) min.	60–75 % of peak at C.O. or 52 bar (750 psi) min.	60–75 % of peak at C.O. or 52 bar (750 psi) min.	60–75 % of peak at C.O. or 52 bar (750 psi) min.
Hold pressure (2 nd stage)	40–50 % of peak at C.O. or 35 bar (500 psi) min.	40–50 % of peak at C.O. or 35 bar (500 psi) min.	40–50 % of peak at C.O. or 35 bar (500 psi) min.	40–50 % of peak at C.O. or 35 bar (500 psi) min.	40–50 % of peak at C.O. or 35 bar (500 psi) min.
Back pressure	3.4–6.9 bar (50–100 psi)	3.4–6.9 bar (50–100 psi)	3.4–6.9 bar (50–100 psi)	3.4–6.9 bar (50–100 psi)	3.4–6.9 bar (50–100 psi)

Time					
Injection (fill) time	1.0–2.0 seconds	1.0–2.0 seconds	0.5–1.5 seconds	1.0–2.0 seconds	0.5–1.5 seconds
Pack time	0.5–1.0 seconds	0.5–1.0 seconds	0.5–1.0 seconds	1.0–1.5 seconds	0.5–1.0 seconds
Hold time	5.0–8.0 seconds	7.0–10.0 seconds	7.0–10.0 seconds	9.0–12.0 seconds	4.0–7.0 seconds
Cooling time	Part dependent	Part dependent	Part dependent	Part dependent (longer)	Part dependent
Injection speed	Medium – fast	Medium – fast	Medium – fast	Medium – fast	Medium – fast
Position ²					
Shot size	Part dependent	Part dependent	Part dependent	Part dependent	Part dependent
Transfer position (cut-off)	95–99% of full part	95–99% of full part	95–99% of full part	95–99% of full part	95–99% of full part
Decompress	13–25.4 mm (0.5–1.0 inch)	13–25.4 mm (0.5–1.0 inch)	13–25.4 mm (0.5–1.0 inch)	13–25.4 mm (0.5–1.0 inch)	13–25.4 mm (0.5–1.0 inch)
Cushion	3.2–6.4 mm (0.12–0.25 inch)	3.2–6.4 mm (0.12–0.25 inch)	3.2–6.4 mm (0.12–0.25 inch)	3.2–6.4 mm (0.12–0.25 inch)	3.2–6.4 mm (0.12–0.25 inch)

¹ Processing conditions listed are for typical start-up conditions for comparison purposes. Most applications are part dependent and will require process adjustment after start-up.

² Use “Screw Position” to switch from 1st stage injection (Velocity Control) to 2nd stage injection (Pressure Control).

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia Pacific



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products. Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks are property of the companies that comprise Solvay Group or their respective owners.

© 2015 Solvay Specialty Polymers. All rights reserved. D X | R 01/2015 | Version 1.0