

# Tecnoflon® PFR 70-BA4

## Perfluoroelastomer Compound

Tecnoflon® PFR 70-BA4 is a 70 Shore A black, FDA compliant, chemical resistant perfluoroelastomer (FFKM) compound based on Tecnoflon® PFR 94. It offers the widest range of aggressive media sealing capabilities along with excellent compression set values.

It is suitable to most applications in temperature ranging from -10 °C to 230 °C, offering outstanding resistance to aggressive media such as acids, caustics, ketones, aldehydes, esters, ethers, methanol, solvents, sour gases, amines, hydrocarbons, steam, hot water, ethylene and propylene oxide and mixed process streams. Moreover it was specifically developed to cope with a wide range of potent active pharmaceutical ingredients (API's) and aggressive cleaning agents, being especially suited to withstand steam-in-place (SIP) and clean-in-place (CIP) procedures.

Tecnoflon® PFR 70-BA4 was specifically designed to manufacture elastomeric stators for progressing cavity pumps, working in aggressive chemical environments or in the food processing industry. Furthermore it can be

transformed into virtually any kind of elastomeric sealing element, including O-rings, gaskets, valve bodies, butterfly valves, metal bonded parts, diaphragms, profiles, etc.

These sealing elements can be used in mechanical seals, pumps, compressors, valves, reactors, mixers, sprayers, dispensers, quick-connect couplings, controls, instrumentation, etc. in the chemical and petrochemical industry, hydrocarbon processing, petroleum exploration and extraction, food processing, the pharmaceutical and bio-analytical industry, the aerospace and semiconductor manufacturing industries.

### Handling and safety

Normal care and precautions should be taken to avoid skin contact, eye contact and inhaling of fumes. Smoking is prohibited in working areas. Wash hands before eating or smoking. For complete health and safety information, please refer to the material safety data sheet.

### Basic characteristics of the compound are as follows:

Property	Typical Value	Unit	Test Method
ML (1+10') at 121 °C	39		
Specific gravity	2.23	g/cm <sup>3</sup>	ASTM D792
Color	Black		
Packaging/form	1 kg /	Slabs	

# Tecnoflon® PFR 70-BA4

## Perfluoroelastomer Compound

### Typical rheological and physical properties

Property	Typical Value	Unit	Test Method
<b>MDR 12 min at 160°C arc 0.5°</b>			ASTM D6601
ML	0.5	lb·in	
MH	23.0	lb·in	
t <sub>s2</sub>	60	s	
t' <sub>50</sub>	95	s	
t' <sub>90</sub>	232	s	
<b>MDR 12 min at 150°C arc 0.5°</b>			ASTM D6601
ML	0.6	lb·in	
MH	20.7	lb·in	
t <sub>s2</sub>	140	s	
t' <sub>50</sub>	235	s	
t' <sub>90</sub>	485	s	

### Mechanical Properties

	Typical Value	Unit	Test Method
<b>Press cure: 10 min at 150°C, post cure: 4 h at 230°C</b>			
100% modulus	6.0	MPa	ASTM D412C
Tensile strength	16.2	MPa	
Elongation at break	180	%	
Hardness	70	Shore A	ASTM D2240
<b>Compression set, 25% deformation, 70 h at 200°C</b>			
#214 O-ring	25	%	ASTM D 395 Method B

### Chemical resistance overview

	Volume Swelling
Inorganic acids	< 10%
Organic acids	< 10%
Alkalis	< 10%
Amines (RT)	< 10%
Hot amines (> 70°C)	10 – 30%
Water/Steam	< 10%
Ketones	< 10%
Esters	< 10%
Ethers	< 10%
Aldehydes	< 10%
Alcohols	< 10%
Hydrocarbons	< 10%
Sour gas	< 10%
Lubricants	< 10%

# Tecnoflon® PFR 70-BA4

## Perfluoroelastomer Compound

### Food and pharma applications

Tecnoflon® PFR 70-BA4 is intended for repeated use in food processing equipment and to be in contact with food types I through VII Table – Types of Raw and Processed Food. The base perfluoroelastomer is registered in the FDA Inventory of Effective Food Contact Substances (FCS) Notifications, being the subject of Food Contact Notification (FCN #128).

See the list of effective notifications for FCN available on the Agency's website at:  
<http://www.accessdata.fda.gov/scripts/fcn/fcnNavigation.cfm?rpt=fcsListing>

### Types of Raw and Processed Foods

- I. Nonacid, aqueous products; may contain salt or sugar or both (pH above 5.0).
- II. Acid, aqueous products; may contain salt or sugar or both and include oil-in-water emulsions of low- or high-fat content.
- III. Aqueous, acid or nonacid products containing free oil or fat; may contain salt, and include water-in-oil emulsions of low or highfat content.
- IV. Dairy products and modifications:
  - A. Water-in-oil emulsions, high- or low-fat.
  - B. Oil-in-water emulsions, high- or low-fat.
- V. Low-moisture fats and oil.
- VI. Beverages:
  - A. Containing up to 8 percent of alcohol.
  - B. Non-alcoholic.
  - C. Containing more than 8 percent alcohol.
- VII. Bakery products other than those included under Types VIII or IX of this table:
  - A. Moist bakery products with surface containing free fat or oil.
  - B. Moist bakery products with surface containing no free fat or oil.
- VIII. Dry solids with the surface containing no free fat or oil (no end test required).
- IX. Dry solids with the surface containing free fat or oil.

[www.solvay.com](http://www.solvay.com)

[SpecialtyPolymers.EMEA@solvay.com](mailto:SpecialtyPolymers.EMEA@solvay.com) | Europe, Middle East and Africa

[SpecialtyPolymers.Americas@solvay.com](mailto:SpecialtyPolymers.Americas@solvay.com) | Americas

[SpecialtyPolymers.Asia@solvay.com](mailto:SpecialtyPolymers.Asia@solvay.com) | Asia Pacific



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products. Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks are property of the companies that comprise Solvay Group or their respective owners.

© 2017 Solvay Specialty Polymers. All rights reserved. R 10/2017 | Version 2.0 Design by ahlersheinel.com